



# Autowave<sup>®</sup> MM 338SA

## FOR PROFESSIONAL USE ONLY

| Description                                                                                                                                                                                                                                     |                                                                                                                                 |                                                                                                             |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------|
| <p>Autowave MM 338SA is an one-pack, ready to spray basecoat with a high metallic gloss that it appears like polished aluminium. Autowave MM 338SA is a waterborne basecoat and should be finished with a Sikkens VOC compliant clearcoat..</p> |                                                                                                                                 |                                                                                                             |
|                                                                                                                                                                | <p>Autowave MM 338SA</p> <p>RFU</p>                                                                                             |                                                                                                             |
|                                                                                                                                                                | <p>Stir thoroughly before use</p>                                                                                               |                                                                                                             |
|                                                                                                                                                                | <p>Spray gun set-up:</p> <p>1.2-1.4 mm</p>                                                                                      | <p>Application pressure:</p> <p>1.7-2.2 bar at the air inlet</p> <p>HVLP max 0.6-0.7 bar at the air cap</p> |
|                                                                                                                                                               | <p>5-6 coats</p>                                                                                                                |                                                                                                             |
|                                                                                                                                                              | <p>Between coats</p> <p>Until matt</p>                                                                                          | <p>Before clearcoat application</p> <p>30 minutes at 20°C</p>                                               |
|                                                                                                                                                              | <p>Clearcoat application</p> <p>See clearcoat T.D.S.</p>                                                                        |                                                                                                             |
|                                                                                                                                                              | <p>Use suitable respiratory protection</p> <p>Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator</p> |                                                                                                             |

Read complete TDS for detailed product information

# Autowave<sup>®</sup> MM 338SA

**FOR PROFESSIONAL USE ONLY**

## Description

Autowave MM 338SA is an one-pack, ready to spray basecoat with a high metallic gloss that it appears like polished aluminium. Autowave MM 338SA is a waterborne basecoat and should be finished with a Sikkens VOC compliant clearcoat..

## Suitable substrates

Correctly flashed off wet on wet primers : Colorbuild Plus  
Through cured 2K Topcoats : Autocryl Plus LV

## Products and additives

Autowave MM 338SA


## Basic raw materials

Autowave MM 338SA: Water based polyurethane dispersion

## Mixing




Stir Autowave MM 338SA thoroughly prior to use.



Autowave MM 338SA

Ready For Use

## Viscosity



14-20 seconds DIN cup 4 at 20°C.

## Spray gun set-up / application pressure



Spray gun

Gravity feed

Fluid tip – set-up

1.2-1.4 mm

Application pressure

1.7-2.2 bar at the spray gun air inlet  
HVLP max 0.6-0.7 bar at the air cap


## Pot-life

3 months at 20°C.

# Autowave<sup>®</sup> MM 338SA

**FOR PROFESSIONAL USE ONLY**

## Application process



### Pre-coat application:

Apply Colorbuild Plus (wet on wet) or Autocryl Plus LV according to product TDS specifications and make sure that surface is completely flat. Any irregularity will be immediately visible after basecoat application. For spot repairs dissolve overspray with SRA thinner. These products should be coated with Autowave MM 338SA within 30 minutes after cool down. Do not sand or abrade the applied topcoat.

### Autowave MM 338SA application:

First apply one single thin coat and allow to flash off until matt. Apply a further three to four 70% coats, allowing to flash-off until matt /semi gloss after each coat. Spraying distance should be at least 30 cm.

Allow for at least 30 minutes flash-off before clearcoat application.


## Film thickness

10 µm

## Recoat with

Autoclear LV Superior  
 Autoclear 2.0

## Recoat time



Autowave MM 338SA must be recoated within 24 hours.

## Theoretical Coverage

By using the recommended application the theoretical material usage is  $\pm 6 \text{ m}^2/\text{l}$  RTS mixture.

*The practical material usage depends on many factors i.e. shape of the object, roughness of the surface, application techniques, pressure, method and application circumstances.*

## Cleaning of equipment

Autowave Guncleaner

## VOC

### 2004/42/IIb(d)(420)420

The EU limit value for this product (product category: IIB.d) in ready to use form is; 420 g/liter of VOC. The VOC content of this product in ready to use form is 420 g/liter RTS mixture.

## Product storage

Product shelf-life is determined when products are stored unopened at 20°C. Avoid extreme temperature fluctuation.

- o Product shelf life data see TDS S9.01.02

# Autowave<sup>®</sup> MM 338SA

FOR PROFESSIONAL USE ONLY

**Akzo Nobel Coatings LTD**

**Address:** Unit 2B, Didcot Park  
Churchward, Southmead Industrial Estate  
Didcot, Oxfordshire, OX11 7HB  
**Tel:** +44 (0)1235 862226

**FOR PROFESSIONAL USE ONLY**

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

**Head Office**

AkzoNobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.sikkenscr.com](http://www.sikkenscr.com)